

Tipo	Densità apparente Kg/m3 +/- 5%	Resistenza alla compressione CLD 40% Kpa +/- 15%	Resa Elastica % (Val min)	Colore
45 VE	45	1,8 - 2,0	10	Bianco
45 VESNA	45	0,7 - 0,8	10	Arancio / Verde
50VE	50	1,8 - 2,0	10	Bianco / Verde
50 VENA	50	1,8 - 2,0	10	Arancio
50 VECM	50	1,8 - 2,0	10	Argento
50 VECAM	50	1,8 - 2,0	10	Neutro
95 VEHD	90	2,4 - 2,6	10	Giallo
95 VEHDCAM	90	2,4 - 2,6	10	Neutro
95 VENAHDH	95	4,0 - 4,2	10	Neutro

* su richiesta.

I dati riportati nelle Schede Tecniche corrispondono alle medie di produzione e sono basate sulle conoscenze disponibili alla data di emissione.

L'utilizzatore deve assicurarsi della congruità e della completezza delle informazioni in relazione all'uso particolare che ne deve fare.

Pelma S.p.A. si riserva l'eventuale variazione delle caratteristiche tecniche dichiarate.

Ultimo aggiornamento: 15 Maggio 2011

* on application.

The data in the table above correspond to the average production data and are written according to the data available at the moment of their certification.

The users have to know all the information about the products in proportion to the particular usage they intend to do with them.

Pelma S.p.A. reserves the right about possible variations of the declared thechnical features.

Last update: 15 Maggio 2011